

GUARDIAN® ANSI/ASSP Z359.11-2021

Pure Safety Group, Inc.
607 East Sam Houston Pkwy S
Suite 800, Pasadena, TX 77053

Test Report Number: 202406143740726
Job Number: Test 175, Test 150
Product SKU#: 3740726
Product Type: Full Body Harness
Product Description: Harness, Series Arc Flash, Sternal D, QC-QC, Size M-L
Testing Standard: ANSI/ASSP Z359.11-2021 Safety Requirements for Full Body Harnesses
Date(s) of Manufacture: 4/01/2024
Date(s) of Testing: 4/08/2024, 4/16/2024, 4/17/2024

REQUIREMENT VERIFICATION

<u>Requirement Description</u>	<u>Clause/Section</u>	<u>Result</u>
General Requirements	3.1 Design Requirements	Meets or Exceeds
Markings and Instructions	5. Markings and Instructions	Meets or Exceeds

QUALIFICATION TESTING

<u>Test Description</u>	<u>Test Date</u>	<u>Clause/Section</u>	<u>Result</u>
Dynamic Performance FF (Dorsal)	4/16/2024	4.3.3 Dynamic Feet First Drop Test	Pass
Dynamic Performance FF (Sternal)	4/17/2024	4.3.3 Dynamic Feet First Drop Test	Pass
Dynamic Performance HF (Dorsal)	4/17/2024	4.3.4 Dynamic Head First Drop Test	Pass
Static Strength FF (Dorsal)	4/17/2024	4.3.5 Static Feet First Test	Pass
Static Strength FF (Sternal)	4/17/2024	4.3.5 Static Feet First Test	Pass
Fall Arrest Indicator (Dorsal)	4/17/2024	4.3.6.2 Alternate Static Test Method	Pass
Static Lanyard Parking Attachment	4/17/2024	4.3.7 Static Feet First Test for Lanyard Parking Attachment Element	Pass
Breaking Strength	4/08/2024	7.1.1 FED-STD-171A/4108, Strength and Elongation Breaking; Textile Webbing, Tape and Braided Items	Pass
Abrasion Test	4/08/2024	7.1.2 FED-STD-171A/5309, Abrasion Resistance of Textile Webbing	Pass

This test report covers these additional products:

3740725, 3740727, 3740728, 3740733, 3740734, 3740735, 3740736

Please contact quality@guardianfall.com for signed report.

TEST EQUIPMENT		
EQUIPMENT	MODEL	SERIAL
Stopwatch	1235C26	200355861
Measuring Tape (Pasadena)	TX1-25	20243699
Test Torso	220 lb	TOR01
Scale	Totalcomp	02314063019
Digital Protractor	950-317	170400992
Load Cell	1220ACK-5K-B	1071229A
Load Cell	1210ACK-10K-B	229097A
Load Cell	1220ACK-25K-B	347989A

Notes

3.1 Design Requirements		
3.1.1	Values. In this standard, values for measurement are followed by a metric equivalent in parentheses, but only the first stated value shall be regarded as the requirement. Values in parentheses may be approximate.	
3.1.1.1	Tolerances. Unless otherwise specified, the values stated in this standard are expressed as nominal values. Except for temperature limits, values which are not stated as maxima or minima shall be subject to a tolerance of $\pm 5\%$. Unless otherwise specified, the ambient temperature for testing shall be between 35°F (1.7°C) and 100°F (37.7°C) and the temperature limits shall be subject to an accuracy of $\pm 2^\circ\text{F}$ ($\pm 1^\circ\text{C}$).	
3.1.2	FBHs shall permanently incorporate a dorsal attachment element described in 3.2.1. FBHs may contain any combination of other elements but limited to those described in Section 3.2. Additionally, FBHs shall permanently include a load bearing sub-pelvic strap, except those described in 3.1.14.	Meets or Exceeds
3.1.3	Shoulder straps on FBHs shall come together at the dorsal location and either cross, be connected by webbing that meets the requirements of Section 3.3 or attach with a connector meeting the requirements of ANSI/ASSP Z359.12.	Meets or Exceeds
3.1.4	FBHs shall permanently incorporate a waist belt or back strap, or other means of controlling the separation of the shoulder straps on the back of the FBH. When the FBH is mounted per manufacturer's instructions onto the test torso defined in 4.2.2, some portion of the back strap or waist belt shall be located between datum levels G and K.	Meets or Exceeds
3.1.5	Modular components or assemblies for FBHs designed for the removal of different attachment elements (such as suspension seats or belts) shall meet the specific attachment element requirements of Section 3.2 while attached to a compatible FBH.	Meets or Exceeds
3.1.5.1	Modular components shall be attached to the harness using connections that meet Section 3.3.3, and those connections shall have a minimum breaking strength of 5,000 pounds (22.2kN). Connections may be a single choked connection as in an attachment element extender. If buckles are used, they must meet ANSI/ASSP Z359.12 and at least be used in pairs.	Meets or Exceeds
3.1.5.2	When attached to the FBH, an attachment element extender shall be no longer than 24 inches (610mm). This distance shall be measured from the new bearing point of the extended attachment element, along the extender's length to a point on the main body of the FBH which would be adjacent to the user's body when donned.	Meets or Exceeds
3.1.6	For FBHs integrated into a vest or other garment, the design of the garment shall allow visual inspection of the FBH.	NA
3.1.7	All FBHs shall be equipped with a visual indicator that will deploy during dynamic testing defined in 3.2.1.3.1 and 3.2.1.3.2, when attached to the dorsal attachment element. All indicators shall be located where they can be visually inspected.	Meets or Exceeds
3.1.7.1	If visual indicators are present on other attachment elements of the FBH, they must activate when tested in accordance with 4.3.6.	Meets or Exceeds
3.1.8	FBH with attached connecting subsystem combinations shall meet the requirements of ANSI/ASSP Z359.11 for the FBH and the appropriate Z359 component standard for the attached subsystem(s) when tested respectively. All elements that are included in the combination shall be qualified with either the FBH or the connecting subsystem in the same configuration as they would be when integrated. Any combinations that cannot be separated and tested individually are outside the scope of this standard and cannot be marked as meeting ANSI/ASSP Z359.11. A specific example of this configuration is reviewed in section 3.1.8.1.	NA

Notes

3.1.8.1	FBH with Integral Energy Absorber. A FBH that includes an energy absorber or energy absorbing lanyard permanently connected can be marked to ANSI/ASSP Z359.11.	
	1. Samples of the harness and energy absorber or energy absorbing lanyard shall be tested independently via procedures and quantities from their respective standards ANSI/ASSP Z359.11 and ANSI/ASSP Z359.13.	NA
	2. The energy absorber or energy absorbing lanyard shall be tested with the connector used in the full body harness.	NA
	3. The harness and energy absorber or energy absorbing lanyard shall be marked and labeled per their most recent respective standards ANSI/ASSP Z359.11 and ANSI/ASSP Z359.13.	NA
3.1.9	All FBHs shall include strap retainers (keepers) or other components which serve to control the loose ends of straps.	Meets or Exceeds
3.1.10	All FBHs shall include at least one lanyard parking attachment element having a disengagement load of not more than 120 pounds (0.5kN) when tested in accordance with 4.3.7. Testing of multiple lanyard parking attachment elements of the same design is not required.	Meets or Exceeds
3.1.11	It shall not be possible to remove elements of the FBH that support the shoulders/upper torso from those that support the legs/lower torso.	Meets or Exceeds
3.1.12	Single point attachment elements shall be located laterally within 2 inches (51mm) of the vertical centerline of the FBH.	Meets or Exceeds
3.1.13	Sternal attachments that consist of two elements intended to be connected at a single point for use shall be fixed and not adjustable vertically. Both elements shall be clearly marked to only be used together.	Meets or Exceeds
3.1.14	FBHs that do not include a sub-pelvic strap shall incorporate both frontal and sternal attachment elements, an integral waist belt and leg loop suspension straps (satisfying the requirements specified in 3.3), two at the front and two at the rear, all integrally attached to the waist belt (see Figure 1d).	NA

Notes

5		
Markings and Instructions		
5.1		
Marking Requirements		
5.1.1	Markings shall be in English	Meets or Exceeds
5.1.2	The legibility and attachment of required markings shall be designed to endure for the life of the component, subsystem or system being marked. When pressure-sensitive labels are used, they shall comply with the applicable provision of 7.2.1. When labels are concealed, a permanent marking shall be visible to the unaided eye that describes how to access the labels.	Meets or Exceeds
5.1.3	Full body harnesses shall be marked with:	
	a. The material of construction.	Meets or Exceeds
	b. The size or range of sizes.	Meets or Exceeds
	c. Part number and/or model designation.	Meets or Exceeds
	d. The month and year of manufacture.	Meets or Exceeds
	e. The manufacturer's name or logo.	Meets or Exceeds
	f. An identifying number, unique to each individual FBH produced by the manufacturer.	Meets or Exceeds
	g. A warning to follow manufacturer instructions included with the equipment at the time of shipment from the manufacturer.	Meets or Exceeds
	h. A label permanently attached to the lanyard parking attachment which either states "Park Lanyard Here. See Instructions." verbally or conveys this by means of a pictogram.	Meets or Exceeds
	i. If the harness stretch measurement for the frontal attachment exceeds 18 inches (457mm) in 3.2.3.1.1, then the harness shall include a warning with the stated stretch out distance.	Meets or Exceeds
	j. If the FBH includes an integrated D-ring extender, a warning shall be included on the D-ring extender that increased free fall should be considered when using this product.	Meets or Exceeds
	k. Applicable pictograms in Figure 12 with a minimum height of 0.8 inch (20mm) or applicable pictograms from CSA Z259.10-18 Figure 1-Figure 8.	Meets or Exceeds
	l. A label as defined in Figure 11a and 11b:	Meets or Exceeds
	1. The label shall be placed in a prominent location on the FBH.	Meets or Exceeds
	2. If the label is part of a label pack or book, the label shall be placed so that the user will see it first.	Meets or Exceeds
	3. The label may be modified to include the mark of the qualification body and may include a part number located on the label outside of the border as needed by the manufacturer as defined in Figure 11a and 11b.	Meets or Exceeds
5.2		
Instruction Requirements		
5.2.1	Instructions shall be provided to the user in English and affixed to the equipment at the time of shipment from the manufacturer.	Meets or Exceeds

5.2.2	Instructions shall contain the following information:	
	a. Annex A in its entirety, either incorporated throughout the manufacturer's instructions, as an appendix to the manufacturer's instructions, or separately provided with the product along with the manufacturer's instructions.	Meets or Exceeds
	b. A statement that the manufacturer's instructions shall be provided to the users.	Meets or Exceeds
	c. Manufacturer's name, address and telephone number.	Meets or Exceeds
	d. Manufacturer's part number and/or model designation for the equipment.	Meets or Exceeds
	e. Intended use and purpose of the equipment.	Meets or Exceeds
	f. Length of FBH stretch HS, and warning to include other factors such as D-ring/connector length, settling of the user's body and all other contributing elements when calculating fall clearance.	Meets or Exceeds
	g. Proper method of use and limitations of the equipment.	Meets or Exceeds
	h. Illustrations showing locations and markings on the equipment.	Meets or Exceeds
	i. An illustration demonstrating the load indicator before and after deployment.	Meets or Exceeds
	j. Reproduction of printed information on all markings.	Meets or Exceeds
	k. Inspection procedures (including frequency) required to assure the equipment is in serviceable condition and operating correctly.	Meets or Exceeds
	l. Criteria for discarding equipment that fails inspection.	Meets or Exceeds
	m. Procedures for cleaning, maintenance and storage.	Meets or Exceeds
	n. Reference to ANSI/ASSP Z359.11 (full body harnesses) and applicable regulations governing occupational safety.	Meets or Exceeds
	o. Acceptable use for all attachment elements (see Annex A).	Meets or Exceeds
5.2.3	Instructions shall require that only the equipment manufacturer, or persons or entities authorized in writing by the manufacturer, make repairs to the equipment.	Meets or Exceeds
5.2.4	Instructions shall require the user to remove equipment from service if it has been subjected to the forces of arresting a fall and will include information on inspection of load indicators.	Meets or Exceeds
5.2.5	Instructions shall require the user to have a rescue plan and the means at hand to implement it when using the FBH for fall arrest.	Meets or Exceeds
5.2.6	Instructions shall provide warnings against:	
	a. Altering equipment.	Meets or Exceeds
	b. Misusing equipment.	Meets or Exceeds
	c. Using combinations of components or subsystems, or both, which may affect or interfere with the safe function of each other.	Meets or Exceeds
	d. Exposing the equipment to chemicals, heat, flames or other environmental conditions, which may produce a harmful effect and to consult the manufacturer in case of doubt.	Meets or Exceeds
	e. Using the equipment around moving machinery and electrical hazards.	Meets or Exceeds
	f. Using the equipment near sharp edges or abrasive surfaces.	Meets or Exceeds
	g. Exposure to light (UV degradation).	Meets or Exceeds

4.3.3 Dynamic Feet First Drop Test - Dorsal Requirements per Section 3.2.1.3.1

- a) For an FBH with a sliding dorsal attachment element, position the bearing point of the attachment element on the FBH in accordance with manufacturer's instructions.
- b) Attach the hoist/quick-release mechanism to the neck of the test torso and raise as needed to attach the test lanyard from the point of the test anchorage to the attachment element of the FBH using test shackles. Connection to bilateral attachment elements shall be through the use of the test yoke described in 4.2.8, except those described in 3.1.13, which will be connected at a single point.
- c) Using the hoist, lower the torso to an elevation where all slack is removed from the test lanyard and connecting components, but not placing a load on the attachment element.
- d) For dorsal, sternal and frontal attachment elements, measure and record the initial height (HI) as the vertical distance from the lowest point on the test torso to the floor.
- e) Raise the torso to a height necessary to apply a peak impact load of not less than 3,600 pounds (16kN) to the attachment element(s) of the FBH when released.
- f) Release the test torso and evaluate the FBH in accordance with requirements in 3.2 for the attachment element(s) being tested.
- g) Measure and record the MAF. Any failure above 4,000 pounds (17.7kN) negates the test, and the test has to be repeated; however, any pass above 3,600 pounds (16kN) is acceptable.
- h) For dorsal, sternal and frontal attachment elements, measure and record the final height (HF) as the vertical distance from the lowest point on the test torso to the floor, post fall. To calculate FBH stretch (HS): $HS = HI - HF$.

4.3.3 Dynamic Feet First Drop Test - Dorsal Requirements per Section 3.2.1.3.1

Samples	Sample # 01	Sample # 02	Sample # 03
Drop Height (in.)	54	48	36
Max Arrest Force >3,600 lb	4994.41	4974.30	4986.79
Hi - Initial Height (in.)	85.5	84.75	85.25
Hf - Final Height (in.)	75.25	74.0	75.0
FBH successfully arrested test torso?	Yes	Yes	Yes
FBH shall support test torso for 5 min post fall	Yes	Yes	Yes
FBH shall support test torso at <30°	0	1	4
At least one fall arrest indicator deployed visibly and permanently	Yes	Yes	Yes
FBH stretch <18" or that which is stated by mfg - whichever is less	10.25	10.25	10.25
Result/Assessment	Pass	Pass	Pass

Notes

4.3.3 Dynamic Feet First Drop Test - Sternal

Requirements per Section 3.2.2.3.1

- a) For an FBH with a sliding dorsal attachment element, position the bearing point of the attachment element on the FBH in accordance with manufacturer's instructions.
- b) Attach the hoist/quick-release mechanism to the neck of the test torso and raise as needed to attach the test lanyard from the point of the test anchorage to the attachment element of the FBH using test shackles. Connection to bilateral attachment elements shall be through the use of the test yoke described in 4.2.8, except those described in 3.1.13, which will be connected at a single point.
- c) Using the hoist, lower the torso to an elevation where all slack is removed from the test lanyard and connecting components, but not placing a load on the attachment element.
- d) For dorsal, sternal and frontal attachment elements, measure and record the initial height (HI) as the vertical distance from the lowest point on the test torso to the floor.
- e) Raise the torso to a height necessary to apply a peak impact load of not less than 3,600 pounds (16kN) to the attachment element(s) of the FBH when released.
- f) Release the test torso and evaluate the FBH in accordance with requirements in 3.2 for the attachment element(s) being tested.
- g) Measure and record the MAF. Any failure above 4,000 pounds (17.7kN) negates the test, and the test has to be repeated; however, any pass above 3,600 pounds (16kN) is acceptable.
- h) For dorsal, sternal and frontal attachment elements, measure and record the final height (HF) as the vertical distance from the lowest point on the test torso to the floor, post fall. To calculate FBH stretch (HS): $HS = HI - HF$.

4.3.3 Dynamic Feet First Drop Test - Sternal

Requirements per Section 3.2.2.3.1

Samples	Sample # 04	Sample # 05	Sample # 06
Drop Height (in.)	54	56	56
Max Arrest Force >3,600 lb	3891.12	4073.29	3809.48
Hi - Initial Height (in.)	89.5	89.0	89.0
Hf - Final Height (in.)	78.0	78.0	78.5
FBH successfully arrested test torso?	Yes	Yes	Yes
FBH shall support test torso for 5 min post fall	Yes	Yes	Yes
FBH shall support test torso at <50°	24	25	26
At least one fall arrest indicator deployed visibly and permanently	Yes	Yes	Yes
FBH stretch <18" or that which is stated by mfg - whichever is less	11.5	11.0	10.5
Result/Assessment	Pass	Pass	Pass

4.3.4 Dynamic Head First Drop Test - Dorsal

Requirements per Section 3.2.1.3.2

- a) For a FBH with a sliding dorsal attachment element, position the bearing point of the attachment element on the FBH 8 inches $\pm$ 1 inch (200mm $\pm$ 25mm) below the top of the shoulder module (datum level A of Figure 5) on the test torso or at the maximum lowest position on the FBH.
- b) Attach the hoist/quick-release mechanism to the crotch of the test torso and raise as needed to attach the test lanyard from the point of the test anchorage to the attachment element of the FBH using test shackles.
- c) Using the hoist, lower the torso to an elevation where all slack is removed from the test lanyard and connecting components, but not placing a load on the attachment element.
- d) Raise the torso to a height of 6 feet (1.8m) or to a height necessary to apply a peak impact load of not less than 3,600 pounds (16kN) to the attachment element(s) of the FBH when released, whichever is less.
- e) Release the test torso and evaluate the FBH in accordance with requirements in 3.2 for attachment element(s) being tested.
- f) Measure and record the MAF. Any failure above 4,000 pounds (17.7kN) would negate the test and would need to be repeated; however, any pass above 3,600 pounds (16kN) or with a drop height of 6 feet (1.8m) or greater is acceptable.

4.3.4 Dynamic Head First Drop Test - Dorsal

Requirements per Section 3.2.1.3.2

Samples	Sample # 07	Sample # 08	Sample # 09
Drop Height (in.)	72	72	72
Max Arrest Force >3,600 lb	4218.26	2864.92	2804.60
FBH successfully arrested test torso?	Yes	Yes	Yes
FBH shall support test torso for 5 min post fall	Yes	Yes	Yes
FBH shall support test torso <30°	1	0	2
Min. one fall arrest indicator deployed visibly and permanently	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

4.3.5 Static Feet First Test - Dorsal Requirements per Section 3.2.1.3.3

- Secure the crotch of the test torso to the static test equipment ensuring the direction of the pull on the attachment simulates a feet first fall.
- Connect the attachment element(s) to the static test equipment using either a test lanyard or test yoke as appropriate.
- Prior to loading the FBH, mark the location of buckles and adjusters as needed to facilitate measurement of tearing or slippage.
- Apply a load of 3,600 pounds (16kN) to the attachment elements and maintain the load for a period of 1 minute.
- Release the load and evaluate the FBH in accordance with requirements in 3.2 for the attachment element being tested.

4.3.5 Static Feet First Test - Dorsal Requirements per Section 3.2.1.3.3

Samples	Sample # 10	Sample # 11	Sample # 12
FBH maintained test torso?	Yes	Yes	Yes
Slippage through any adjuster >1 in?	0	0	0
Tongue buckle tears >1 in. or to the adjacent eyelet?	0	0	0
Straps tear (other than those above)?	0	0	0
Result/Assessment	Pass	Pass	Pass

4.3.5 Static Feet First Test - Sternal Requirements per Section 3.2.1.3.3

- Secure the crotch of the test torso to the static test equipment ensuring the direction of the pull on the attachment simulates a feet first fall.
- Connect the attachment element(s) to the static test equipment using either a test lanyard or test yoke as appropriate.
- Prior to loading the FBH, mark the location of buckles and adjusters as needed to facilitate measurement of tearing or slippage.
- Apply a load of 3,600 pounds (16kN) to the attachment elements and maintain the load for a period of 1 minute.
- Release the load and evaluate the FBH in accordance with requirements in 3.2 for the attachment element being tested.

4.3.5 Static Feet First Test - Sternal Requirements per Section 3.2.1.3.3

Samples	Sample # 13	Sample # 14	Sample # 15
FBH maintained test torso?	Yes	Yes	Yes
Slippage through any adjuster >1 in?	0	0	0
Tongue buckle tears >1 in. or to the adjacent eyelet?	0	0	0
Straps tear (other than those above)?	0	0	0
Result/Assessment	Pass	Pass	Pass

4.3.6.2 Fall Indicator Test Requirements per Sections 3.2.1.3.4 & 3.2.2.3.3

- Secure the crotch of the test torso to the static test equipment ensuring the direction of the pull on the attachment simulates a feet first fall.
- Connect the attachment element(s) to the static test equipment using either a test lanyard or test yoke as appropriate
- Apply a load to the attachment element until a maximum load of 900 pounds (4.0 kN) is achieved as indicated by the static tensile test equipment, or the indicator deploys, whichever occurs first
- Release the test torso and evaluate the FBH in accordance with requirements in 3.2 for the attachment elements being tested

4.3.6.2 Fall Indicator Test - Dorsal Requirements per Sections 3.2.1.3.4

Samples	Sample # 16	Sample # 17	Sample # 18
One Fall Arrest Indicator Deployed?	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

4.3.7 Static Feet First Test for Lanyard Parking Attachment Element Requirements per Section 3.1.10

- Secure the crotch of the test torso to the static test equipment ensuring the direction of the pull on the attachment simulates a feet first fall.
- Connect the attachment element to the static test equipment using a test lanyard.
- Apply and steadily increase the load until the connection between the lanyard parking attachment and the test lanyard separates completely.
- Record the maximum force applied to the attachment element and compare this with the requirement given in 3.1.10.

4.3.7 Static Feet First Test for Lanyard Parking Attachment Element Requirements per Section 3.1.10

Samples	Sample # 19	Sample # 20	Sample # 21
Parking element broke under 120 lb?	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass

7.1.1 Breaking Strength
Requirements per Section 3.3.1.2 & 7.1.1

- a) Per FEDSTD191A Method 4108, Please each 54 in. (1372 mm) sample in the static test bed with the long dimension parallel to the application of the load
- b) Apply force at a rate of 3.0 ± 1.0 in. (76 ± 25 mm) per minute until the sample is ruptured
- c) When the sample ruptures, the breaking load shall be recorded
- d) Evaluate in accordance with the requirements in 3.3.1.2

7.1.1 Breaking Strength
Requirements per Section 3.3.1.2 & 7.1.1

Samples	Sample # 22	Sample # 23	Sample # 24	Sample # 25	Sample # 26
SKU# of Strap	1401065	1401065	1401065	1401065	1401065
Description	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR
Load Applied pre-abrasion >5,000 lb	10182.4	10288.5	10626.1	9916.5	9922.4
Result/Assessment	Pass	Pass	Pass	Pass	Pass

7.1.2 Abrasion Test
Requirements per Section 3.3.1.5 & 7.1.2

- a) Per FEDSTD191A Method 5309, place each 54 in. (1372mm) sample in abrasion tester with a 5.2 lb +/- .02 oz weight attached to the end
- b) Secure sample to 16in. (406 mm) drum
- c) Pass the sample over the .250 +/- .001 in. (6.35 +/- .03 mm) steel hexagonal rod with a radius of .020 +/- .004 in. (.5 +/- .1mm) at a 85 +/- 2 degree angle
- d) Oscillate the drum so the specimen traverses 12+/-1 in. (305 +/- 25 mm) over the rod at a rate of 60 +/- 2 strokes (30 +/- cycles) per minute for 5,000 strokes (2,500 cycles).
- e) Per 3.3.1.5 & 7.1.1, after abrasion, the sample shall be pulled at a rate of 3 +/- 1in. (76 +/- 25 mm) per minute until it is ruptured
- f) When sample ruptures, the breaking (actual) load shall be recorded

7.1.2 Abrasion Test
Requirements per Section 3.3.1.5 & 7.1.2

Samples	Sample # 27	Sample # 28	Sample # 29	Sample # 30	Sample # 31
SKU# of Strap	1401065	1401065	1401065	1401065	1401065
Description	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR	WEBBING, 1.75", NY-LON OVER KEVLAR
Load applied post-abrasion >3,600 lb	6084.6	5500.5	6419.3	6383.4	6072.7
Result/Assessment	Pass	Pass	Pass	Pass	Pass

Pictured: 3740725
Represents part #s 3740725 - 3740728



Pictured: 3740734
Represents part #s 3740734 - 3740736



Notes

Labels
Represents all part #s

1500386 Rev. A-1

ANSI Z359.11-2021
ANSI Z359 recognizes the use of this
harness only within the capacity range of:
130-310 lbs

1500386 Rev. A-2

Compliant with:
ASTM F887
OSHA 1910.140
OSHA 1926.502
ANSI Z359.11-2021

Cumplir con:
ASTM F887
OSHA 1910.140
OSHA 1926.502
ANSI Z359.11-2021

Conforme aux normes de:
ASTM F887
l'OSHA 1910.140
de l'OSHA 1926.502
de l'ANSI Z359.11-2021

1500386 Rev. A-3


GUARDIAN
guardianfall.com
**Series Arc Flash
Harness**

Material: Kevlar®, Nomex®, nylon, aluminum, steel
Materiales: Kevlar®, Nomex®, nylon, aluminio, acero
Matériaux: Kevlar®, Nomex®, nylon, aluminium, acier

Designed, tested and assembled in USA

Diseñado, probado y ensamblado en los
Estados Unidos

Conçu, testé et assemblé aux États-Unis

**DO NOT REMOVE LABELS
NO DESPRENDA LAS ETIQUETAS
NE RETIREZ PAS LES ÉTIQUETTES**

1500386 Rev. A-4

Make only compatible connections. Prior to use, inspect equipment for rips, tears, fraying, or any possible structural deficiency that might compromise the equipment in a fall. Avoid contact with sharp and abrasive surfaces.

Haga solo conexiones compatibles. Antes de usar este equipo, inspecciónelo para detectar desgarres, roturas, deshilachados o cualquier otro defecto estructural que podría poner en peligro el equipo en caso de una caída. Evite el contacto con superficies afiladas y abrasivas.

Ne faites que des connexions compatibles. Avant l'utilisation, inspectez l'équipement pour détecter les accrocs, les déchirures, l'effilochage ou toute défectuosité de structure possible qui pourrait nuire à l'équipement lors d'une chute. Évitez tout contact avec des surfaces tranchantes et abrasives.

1500386 Rev. A-5

▲ WARNING!

Prior to use, understand all manufacturer instructions included with equipment at time of shipment. Improper use of this equipment could result in serious injury or death. IMMEDIATELY remove from service if subjected to a fall or if harness fails inspection.

▲ ADVERTENCIA!

Antes de usar este producto, entienda todas las instrucciones del fabricante que vienen con el equipo. El uso incorrecto del equipo puede causar lesiones graves o muerte. Ponga DE INMEDIATO el equipo fuera de servicio si estuvo expuesto a una caída o si el arnés no pasa la inspección.

▲ AVERTISSEMENT!

Avant l'utilisation, comprenez toutes les instructions du fabricant incluses avec l'équipement au moment de l'expédition. L'utilisation abusive de cet équipement pourrait entraîner des blessures graves ou la mort. Mettez IMMÉDIATEMENT le harnais hors service s'il est soumis à une chute ou s'il ne satisfait pas l'inspection.

1500386 Rev. A-6

User must inspect prior to EACH use. Competent Person must complete formal inspection every 12 months. Competent Person to inspect and initial. Product lifetime is indefinite as long as equipment passes pre-use and Competent Person inspections.

El usuario debe inspeccionar el equipo antes de CADA uso. Una persona competente debe completar una inspección formal al menos cada 12 meses. La persona competente debe inspeccionar y firmar con sus iniciales.

La vida útil del producto es indefinida, siempre que pase las inspecciones previas al uso y las inspecciones de la persona competente.

L'utilisateur doit inspecter l'équipement avant CHAQUE utilisation. Une personne compétente doit effectuer une inspection officielle au moins tous les 12 mois. Elle doit inspecter et apposer ses initiales. La durée de vie du produit est indéterminée à condition que l'équipement soit conforme aux inspections avant l'utilisation et par une personne compétente.

1500386 Rev. A-7

**INSPECTION GRID
CUADRÍCULA DE INSPECCIÓN
GRILLE D'INSPECTION**

Initials:	Date:

Date of First Use:

1500386 Rev. A-8

Refer to below chart for allowed worker weight capacity range per specific fall protection regulation. Always defer to applicable connecting device to determine permitted worker weight capacity range for complete system.

Consulte la siguiente tabla para conocer el rango de capacidad de peso permitido para el trabajador según la regulación específica de protección contra caídas. Siempre deferir a el dispositivo de conexión correspondiente para determinar el rango de capacidad de peso para trabajador permitido para el sistema completo.

Reportez-vous toujours au dispositif de connexion applicable pour déterminer la plage de capacité de charge de travail autorisée pour un système complet. Reportez-vous toujours à la gamme de poids de votre connecteur pour déterminer la capacité du système complet.

	ANSI	OSHA
130-310 lb (59-141 kg)	✓	
100-420 lb (45-191 kg)		✓



Test Report ASTM F887-2020

Pure Safety Group, Inc. dba Guardian Fall
607 East Sam Houston Pkwy S
Suite 800, Pasadena, TX 77053

Test Report Number: 202406143740726
Job Number: K-581029-2403H04-R00, Test 121
Product SKU#: 3740726
Product Type: Full Body Harness
Product Description: Harness, Series Arc Flash, Sternal D, QC-QC, Size M-L
Testing Standard: ASTM F887-2020, 25.5 Harness
Date(s) of Manufacture: 3/01/2024
Date(s) of Testing: 3/14/2024, 3/27/2024, 3/28/2024

REQUIREMENT VERIFICATION

<u>Requirement Description</u>	<u>Clause/Section</u>	<u>Result</u>
Classification	18. Classification	Meets or Exceeds

QUALIFICATION TESTING

<u>Test Description</u>	<u>Test Date</u>	<u>Clause/Section</u>	<u>Result</u>
Electric Arc Testing	3/14/2024	22. After Exposure to an Electric Arc	See Appended Report
Dynamic Performance (Post-Arc, Dorsal, Feet First)	3/27/2024	25.5.2 Drop Test Procedures	Pass
Dynamic Performance (Post-Arc, Dorsal, Head First)	3/27/2024	25.5.2 Drop Test Procedures	Pass
Dynamic Performance (Post-Arc, Sternal, Feet First)	3/28/2024	25.5.2 Drop Test Procedures	Pass

This test report covers these additional products:

3740725, 3740727, 3740728, 3740733, 3740734, 3740735, 3740736

Please contact quality@guardianfall.com for signed report.

TEST EQUIPMENT		
EQUIPMENT	MODEL	SERIAL
Load Cell	1220ACK-5K-B	1071229A
Test Torso	220 lb	TOR01
Scale	Totalcomp	02314063019
Digital Protractor	950-317	170400992
Measuring Tape (Pasadena)	TX1-25	20243699

Notes

18 Classification		
18.1	Harnesses (see Fig. 24) covered under this standard shall be designated as Type A or B as follows:	
18.1.1	Type A—Full body harness.	Meets or Exceeds
18.1.2	Type B—Full body harness with body belt attachment	Meets or Exceeds
18.2	Ordering Information:	
18.2.1	Orders for equipment under this standard should include the following information:	
18.2.1.1	Nomenclature	Meets or Exceeds
18.2.1.2	Type	Meets or Exceeds
18.2.1.3	Material, and	Meets or Exceeds
18.2.1.4	Size. (See Table 4).	Meets or Exceeds
18.2.2	The listing of equipment, type, and sizes is not intended to mean that all shall necessarily be available from the manufacturer; the listing signifies only that, if made, the equipment, types, and sizes shall conform to the details of this standard. Additional designs or modifications of equipment or hardware may be specified by the user for a particular application providing equipment or hardware meets the performance requirements of this standard.	Meets or Exceeds
18.3	Sizing:	
18.3.1	Sizes—Harnesses may be manufactured and designated by the sizes small, medium, large, X-large, and XX-large. The manufacturer's harness design shall accommodate the height and chest sizes shown in Table 4	Meets or Exceeds
18.4	Marking:	
18.4.1	Harnesses manufactured under this standard shall be labeled as meeting this standard providing they satisfy the following requirements:	Meets or Exceeds
18.4.1.1	All load bearing webbing used in the construction of the harness shall have a minimum breaking strength of 7000 lbf (31.14 kN).	Meets or Exceeds
18.4.1.2	All harnesses marked as meeting the requirements of this standard shall also meet all applicable requirements specified in ANSI/ASSE Z359.11-2014, Safety Requirements for Full Body Harnesses.	Meets or Exceeds
18.4.1.3	Harnesses shall meet the qualification testing requirements in Section 22 and 25.5 of this standard.	Meets or Exceeds

Notes

**25.5.2 Drop Test Procedures
(Post-Arc, Dorsal, Feet First)
Requirements per Section 25.5.3**

- a) The drop test is to be done on the samples exposed to the arc test as indicated in Table 5. A new harness may be used for each test
- b) The harness shall be snugly secured about the test mass. One end of the wire rope shall be hooked into the fall arrest attachment and the other to the test structure anchorage point. The quick-release mechanism shall be hooked into the same point.
- c) Raise the mass until the opposite end of the wire rope can be snapped into the test-structure anchorage point. Note the level of the fall arrest attachment point and raise the test mass until the fall arrest attachment point has been raised a distance of 39.4 in. (1 m). The torso shall be lifted to a point no more than 12 in. (305 mm) horizontally from the anchorage.
- d) Release the test mass by means of the quick-release mechanism.
- e) After the drop, the torso is to remain suspended by the harness for a period of 5 min.

**25.5.2 Drop Test Procedures
(Post-Arc, Dorsal, Feet First)
Requirements per Section 25.5.3**

Samples	Sample # 01	Sample # 02	Sample # 03	Sample # 04
Sample passed ASTM F887-20, 22 Electric Arc Testing?	Yes	Yes	Yes	Yes
Sample maintained test torso?	Yes	Yes	Yes	Yes
Load-bearing elements intact?	Yes	Yes	Yes	Yes
Sample maintained <30° post-drop?	1	2	1	1
Sample maintained torso for 5 minutes, post drop?	Yes	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass	Pass

**25.5.2 Drop Test Procedures
(Post-Arc, Dorsal, Head First)
Requirements per Section 25.5.3**

- a) The drop test is to be done on the samples exposed to the arc test as indicated in Table 5. A new harness may be used for each test
- b) The harness shall be snugly secured about the test mass. One end of the wire rope shall be hooked into the fall arrest attachment and the other to the test structure anchorage point. The quick-release mechanism shall be hooked into the same point.
- c) Raise the mass until the opposite end of the wire rope can be snapped into the test-structure anchorage point. Note the level of the fall arrest attachment point and raise the test mass until the fall arrest attachment point has been raised a distance of 39.4 in. (1 m). The torso shall be lifted to a point no more than 12 in. (305 mm) horizontally from the anchorage.
- d) Release the test mass by means of the quick-release mechanism.
- e) After the drop, the torso is to remain suspended by the harness for a period of 5 min.

**25.5.2 Drop Test Procedures
(Post-Arc, Dorsal, Head First)
Requirements per Section 25.5.3**

Samples	Sample # 05	Sample # 06	Sample # 07	Sample # 08
Sample passed ASTM F887-20, 22 Electric Arc Testing?	Yes	Yes	Yes	Yes
Sample maintained test torso?	Yes	Yes	Yes	Yes
Load-bearing elements intact?	Yes	Yes	Yes	Yes
Sample maintained <30°, post-drop?	2	5	2	1
Sample maintained torso for 5 minutes, post drop?	Yes	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass	Pass

**25.5.2 Drop Test Procedures
(Post-Arc, Sternal, Feet First)
Requirements per Section 25.5.3**

- a) The drop test is to be done on the samples exposed to the arc test as indicated in Table 5. A new harness may be used for each test
- b) The harness shall be snugly secured about the test mass. One end of the wire rope shall be hooked into the fall arrest attachment and the other to the test structure anchorage point. The quick-release mechanism shall be hooked into the same point.
- c) Raise the mass until the opposite end of the wire rope can be snapped into the test-structure anchorage point. Note the level of the fall arrest attachment point and raise the test mass until the fall arrest attachment point has been raised a distance of 39.4 in. (1 m). The torso shall be lifted to a point no more than 12 in. (305 mm) horizontally from the anchorage.
- d) Release the test mass by means of the quick-release mechanism.
- e) After the drop, the torso is to remain suspended by the harness for a period of 5 min.

**25.5.2 Drop Test Procedures
(Post-Arc, Sternal, Feet First)
Requirements per Section 25.5.3**

Samples	Sample # 09	Sample # 10	Sample # 11	Sample # 12
Sample passed ASTM F887-20, 22 Electric Arc Testing?	Yes	Yes	Yes	Yes
Sample maintained test torso?	Yes	Yes	Yes	Yes
Load-bearing elements remained intact?	Yes	Yes	Yes	Yes
Sample maintained torso at <50°, post-drop?	25	24	21	27
Sample maintained torso for 5 minutes, post drop?	Yes	Yes	Yes	Yes
Result/Assessment	Pass	Pass	Pass	Pass



EXPOSURE TO AN ELECTRIC ARC

Requesting Agency:

Guardian
607 East Sam Houston Pkwy S
Suite 800
Pasadena, TX 77503

Reference Test Standard:

ELECTRIC ARC TESTS: ASTM F887-20, SECTION 22

Qualification Testing for Exposure to an Electric Arc

Test Report:

K-581029-2403H04-R00

Test Specimen:

Harness, Style 3740726 - HARNESS, SERIES ARC FLASH, STERNAL D, QC-QC,
SIZE M-L, Webbing: Nylon/Kevlar, Black with Yellow Tracers

Result:

As requested, the samples of Guardian Style 3740726 harness with Nylon/Kevlar webbing were exposed to an electrical arc. Based on test results, this harness meets the requirements in Table 1-1. To complete the qualification requirements for ASTM F887-20, the arc exposed test samples shall be submitted to the applicable required drop test specified in section 25.5 or 25.6 as soon as is practically possible by the requesting agency.

Sample Received	Test Date	Report Date
March 6, 2024	March 14, 2024	April 2, 2024

Prepared by

Approved by

Claude Maurice
Technical Specialist, HCL
TD Technologies, Kinectrics

Brian Shiels
Service Line Manager
ArcWear, Kinectrics AES

Revision History

Rev	Description		
00	Initial report creation		
	Issue Date	Prepared by	Approved by
	April 2, 2024	Claude Maurice	Brian Shiels
Rev	Description		
	Issue Date	Prepared by	Approved by

For questions about this test report, please contact Contact.ArcWear@Kinectrics.com

DISCLAIMER

Kinectrics prepared this report as a work of authorship sponsored by their Client. This report has been prepared solely for the benefit of the Client and may not be used or relied upon in whole or in part by any other person or entity without Client permission or without Kinectrics' permission if required by the Contract between Client and Kinectrics Inc. Neither Kinectrics, their client nor any person acting on behalf of them: (a) makes any warranty or representation whatsoever, express or implied, or assumes any legal liability of responsibility for any third party's use, or the results of such use, with respect to (i) the use of any information, apparatus, method, process, or similar item disclosed in this report including the merchantability or fitness for any particular purpose of any information contained in this report or the respective works or services supplied or performed or (ii) that such use does not infringe on or interfere with privately owned rights, including any party's intellectual property; or (b) assumes responsibility for any damages or other liability whatsoever (including any consequential damages resulting from a third party's selection or use of this report or any information, apparatus, method, process, or similar item disclosed.

Copyright © 2024 Kinectrics Inc. All rights reserved.

QUALITY MANAGEMENT

The arc testing performed to the above mentioned Standard is accredited by the Standards Council of Canada (SCC) to conform to the requirements of CAN-P-4E (ISO/IEC 17025:2017). Accreditation by the Standards Council of Canada (SCC) is a mark of competence and reliability

- The test performed does not apply to electrical contact or electrical shock hazard.
- The test result is applicable only to the Test Specimens delivered to Kinectrics, other material, design or color may have a different response.
- It is the clients' responsibility to provide full and accurate information about the items supplied.
- No test is done to validate the fiber content or composition of the test item.
- Photographs of the test specimens and waveforms of the arc current, voltage and calorimeters with the circuit and arc exposure calibration records are available from Kinectrics and provided to the client separately from this report.



1 Test Standard:

Electrical arc test according to ASTM F887-20, Section 22

Standard Specifications for Personal Climbing Equipment, After Exposure to an Electric Arc Evaluation. Specimens are mounted on mannequins having a distance of 30.5 cm (12 inches) from the chest to the centerline of the electrodes. The test standard requires that the finished personal climbing equipment be exposed to a level of $40 \text{ cal/cm}^2 \pm 5 \text{ cal/cm}^2$.

1.1 Test Requirements

Harnesses- The test program requires the specimens be placed on mannequins as normally worn. Sufficient quantities shall be exposed on the front and on the back to meet the drop test requirements of Table 5 of the Standard.

Harness with dorsal attachment only: 4 frontal arc exposure, 4 rear arc exposure (8 samples arc tested).

Harness with front and dorsal attachment: 6 frontal arc exposure, 6 rear arc exposure, (12 samples arc tested).

Harness accessories, loops etc. - Three specimens of each accessory or loop are required to be exposed to the arc.

Energy Absorbing Lanyard - Three specimens of each lanyard are required to be exposed to the arc.

SRL & SRD- Self-retracting devices (SRDs) are not included in the scope of arc exposure test in ASTM F887-20, Section 22. Their test method, number of samples required, and subsequent drop test and criteria has not been established by ASTM. Until the standard is revised, the arc exposure test is based on the requirements for Energy Absorbing Lanyards (non-retracting). The drop test to verify mechanical integrity following the arc exposure will be arranged by the producer based on the applicable drop method followed for such devices.

Other effects as a result for an arc fault such as the noise, light emissions, pressure rise, hot oil, electric shock, the consequences of physical and mental shock or toxic influences are not covered by this standard.

1.2 Acceptance criteria for products exposed to electrical arc:

The procedure outlined in ASTM F887-20 is followed to verify the electric arc performance of the personal climbing equipment. The product is considered as having passed the visual inspection criteria if the parameters defined in Table 1-1 are met. As proof of performance following the arc exposure, the exposed test specimens shall be subjected to a drop test as soon as practical after the arc exposure.

Table 1-1: Visual inspection Criteria for Electric Arc Performance of ASTM F887-20

Parameter	Criterion
Arc Energy	Electrical arc exposure of $40 \text{ cal/cm}^2 \pm 5 \text{ cal/cm}^2$
Ignition	No electric arc ignition.
After-flame Time	Less than 5 seconds on load bearing materials and less than 15 seconds for accessories or non-load bearing components.
Material Performance	Material shall withstand the arc exposure with good integrity and have no melting and dripping of molten materials to the floor of any load bearing material. Non load bearing accessories may exhibit melting and dripping provided they are not ignited while dripping.

2 Test Condition:

The following test circuit parameters and conditions were used.

- Electric arc current: 8 kA rms $\pm 10\%$, 60 Hz
- Open circuit voltage: 2500 V rms $\pm 10\%$, 60 Hz
- Nominal Heat Flux Density: 2100 kW/m^2 ($50 \text{ cal/cm}^2\cdot\text{s}$)
- Arc duration: 0.85 seconds $\pm 0.1 \text{ s}$ to obtain required incident energy
- Electrode gap: 305 mm (12 inches)
- Distance from mannequin to electrode: 305 mm (12 inches)
- Deviations and abnormalities: none

Note: The measurement uncertainty, MU, for the measured values of this test method are well within the requirements of the test standard and are defined on a 95% confidence interval basis over the full test range, as follows:

- Temperature: $\pm 2^\circ\text{C}$
- Arc Current: $\pm 2.5\%$
- Time zero reference: $\pm 3 \text{ ms}$
- Incident Energy: $\pm 1.5\%$
- Voltage: $\pm 2.2\%$

3 Test Sample Description:

The following description of the test sample was provided by the client and confirmed by the sample shown in Figure 3.1.

Sample description:	Harness, Style 3740726 - HARNESS, SERIES ARC FLASH, STERNAL D, QC-QC, SIZE M-L, Webbing: Nylon/Kevlar, Black with Yellow Tracers
Sample identification:	Serial number when available identified in Table 4-1
Manufacturer:	Guardian
Material of webbing:	Nylon/Kevlar, Webbing thickness 2.1 mm
Number of samples tested:	12
Notes:	



Figure 3.1: Guardian Harness, Style 3740726, with label pouch at the back.

4 Test Results:

Two mannequin torsos were placed at 120° in the arc test cage at a distance of 305 mm (12 in) from the electrodes. The samples were placed on each of the two mannequins as shown in Figure 6.1.

Table 4-1a: Summary of Test Results

	Trial # 24-0831		Trial # 24-0832	
Mannequin	A	B	A	B
Serial number	N/A	N/A	N/A	N/A
Exposure area	Front	Back	Front	Back
Incident Energy	41 cal/cm ²	37 cal/cm ²	41 cal/cm ²	38 cal/cm ²
Ignition or Afterflame time	0 s	0 s	0 s	0 s
Melting and Dripping	No	No	No	No
Acceptance Criteria	Meets	Meets	Meets	Meets

Table 4-1b: Summary of Test Results

	Trial # 24-0833		Trial # 24-0834	
Mannequin	A	B	A	B
Serial number	N/A	N/A	N/A	N/A
Exposure area	Front	Back	Front	Back
Incident Energy	40 cal/cm ²	41 cal/cm ²	41 cal/cm ²	41 cal/cm ²
Ignition or Afterflame time	0 s	0 s	0 s	0 s
Melting and Dripping	No	No	No	No
Acceptance Criteria	Meets	Meets	Meets	Meets

Table 4-1c: Summary of Test Results

	Trial # 24-0835		Trial # 24-0836	
Mannequin	A	B	A	B
Serial number	N/A	N/A	N/A	N/A
Exposure area	Front	Back	Front	Back
Incident Energy	40 cal/cm ²	44 cal/cm ²	40 cal/cm ²	40 cal/cm ²
Ignition or Afterflame time	0 s	0 s	0 s	0 s
Melting and Dripping	No	No	No	No
Acceptance Criteria	Meets	Meets	Meets	Meets

4.1 Observations:

Samples having met the visual performance criteria are marked as “Meets”. Samples marked as ‘Fails’ indicate they do not meet the requirements due to long AF time or ignition. Photographs of the samples before and after the arc exposure are shown in Section 6.

Charring was observed on the webbing and exposed material on all samples.

- No afterflame or melting and dripping of any webbing was observed.
- The label packet material was charred and showed some ablation.
- The keepers were heavily charred and broken but no melting or afterflame.

5 Interpretation of Results:

This testing does not assign an arc rating to this product. The purpose of this test is to observe the response characteristics of the lanyards when exposed to an open-air electric arc as described in ASTM F887-20.

Based on test results, this harness meets the requirements in Table 1-1 for ASTM F887-20 section 22. To complete the qualification requirements for ASTM F887-20, the arc tested samples shall be subjected to the applicable required drop test specified in section 25.5 or 25.6 as soon as is practically possible by the requesting agency.

6 Photographs:

The following photographs are representative of the test results observed. Photographs and video of all test samples are provided with this report for review.



Figure 6.1: Sample set up before the arc exposure,



Figure 6.2: Sample after the arc exposure, test 24-0831, A: Left, B: Right.



Figure 6.3: Sample after the arc exposure, test 24-0836, A: Left, B: Right.



Figure 6.4: Label pouch after the arc exposure, test 24-0836



Figure 6.5: Webbing keepers and adjusters after the arc exposure, test 24-0836