
**Double 6" 21FBD6__**

Length 12' - 6" | 8 Panels/Ctn. | 1 Sq./Ctn. | Ctn. Weight: 70 lbs.

**Dutchlap 4.5" 21FB245__**

Length 12' - 1" | 11 Panels/Ctn. | 1 Sq./Ctn. | Ctn. Weight: 83.99 lbs.


Color # | Color

02 White Birch
 11 Classic Sand
 17 Warm Sandalwood
 41 Soft Willow

44 Harbor Stone
 46 Basket Beige
 49 Graphite Grey
 52 Java

61 Artisan Clay
 79 Seagrass
 81 Canyon Brown
 82 Meadow

87 Heritage Red
 89 Hampton Blue
 90 Gray Flannel
 94 Mountain Pine

**Board & Batten" 21FBBB7__**

Length 10' - 0" | 17 Panels/Ctn. | 1 Sq./Ctn. | Ctn. Weight: 60 lbs.

Color # | Color

02 White Birch
 11 Classic Sand
 17 Warm Sandalwood

41 Soft Willow
 44 Harbor Stone
 49 Graphite Grey

61 Artisan Clay
 79 Seagrass
 82 Meadow

Comfort Clad Insulated Vinyl Siding

SCI® Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

Product Test Data

Siding Thickness..... D6 & DL4.5 .046 | B&B .048
 Specific Gravity..... 1.45
 Tensile Strength (PSI)..... 7,154
 Tensile Modulus (PSI)..... 416,900
 IZOD Impact Strength @ 32°F..... Passes per ASTM D3679
 Heat Deflection Temp. @ 264 PSI..... 169°F
 Coefficient of Linear Expansion..... 3.30 x 10⁻⁵
 Warpage..... 0.00"
 Heat Shrinkage..... 0.3%
 Surface Distortion @ 140°F..... 0

Flame Spread Index..... 10
 Fire Rating Class A
 Smoke Developed..... 395
 Fuel Contribution..... 0
 Average Time Of Burning..... Self extinguished
 Average Extent Of Burning..... 2.379 mm
 Weathering..... Passes per ASTM D3679
 Windload Rating for D6* 193 MPH
 Windload Rating for B&B* 117 MPH
 *(Wind Velocity based on IBC)
 Impact Resistance..... Passes per ASTM D3679