


# Data Sheet


## Spiegel Grove® Vinyl Siding

### Classic Character




#### Double 4" 20D4\_\_

Length 12' - 6" | 24 Panels/Ctn. | 2 Sq./Ctn. | 20 Ctns./Crate | Ctn. Weight: 87.08 lbs.



#### Dutchlap 4.5" 20DL45\_\_

Length 12' - 1" | 22 Panels/Ctn. | 2 Sq./Ctn. | 16 Ctns./Crate | Ctn. Weight: 83.99 lbs.




#### Dutchlap 5" 20DL5\_\_

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 14 Ctns./Crate | Ctn. Weight: 82.26 lbs.

#### Color # | Color | Brushed Cedar Woodgrain Finish

02 White Birch	26 Summer Wheat	46 Basket Beige	61 Artisan Clay
11 Classic Sand	41 Soft Willow	47 Slate Blue	79 Seagrass
17 Warm Sandalwood	43 Pebble Clay	49 Graphite Grey	82 Meadow
22 Sunny Maize	44 Harbor Stone	52 Java	86 Nutmeg




#### Double 5" 20D5\_\_

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 15 Ctns./Crate | Ctn. Weight: 82.87 lbs.

#### Color # | Color | Brushed Cedar Woodgrain Finish

02 White Birch	41 Soft Willow	46 Basket Beige	82 Meadow
17 Warm Sandalwood	43 Pebble Clay	47 Slate Blue	86 Nutmeg
22 Sunny Maize	44 Harbor Stone	79 Seagrass	



#### T3.3" 20T333\_\_

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 15 Ctns./Crate | Ctn. Weight: 83.98 lbs.

#### Color # | Color | Brushed Cedar Woodgrain Finish

02 White Birch	43 Pebble Clay	82 Meadow
17 Warm Sandalwood	44 Harbor Stone	86 Nutmeg
22 Sunny Maize	46 Basket Beige	

### Spiegel Grove® Vinyl Siding w/Reinforced Nail Hem

SCI® Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

#### Product Test Data

Siding Thickness..... 040" ± .001"	Heat Shrinkage.....0.3%
Specific Gravity.....1.45	Surface Distortion @ 140°F.....0
Tensile Strength (PSI).....7,154	Flame Spread Index.....10
Tensile Modulus (PSI).....416,900	Fire Rating ..... Class A
IZOD Impact Strength @ 32°F..... Passes per ASTM D3679	Smoke Developed.....395
Heat Deflection Temp. @ 264 PSI.....169°F	Fuel Contribution.....0
Coefficient of Linear Expansion.....3.30 x 10 <sup>-5</sup>	Average Time Of Burning..... Self extinguished
Warpage.....0.00"	Average Extent Of Burning.....2.379 mm
	Weathering..... Passes per ASTM D3679
	Impact Resistance..... Passes per ASTM D3679



Go to [www.vinylsiding.org](http://www.vinylsiding.org) for a current list of certified products and colors.

