


Data Sheet

Universal Soffit

Value Performance





10" Vinyl Soffit Solid - Brushed Finish 32US10SD02

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 75.73 lbs.

10" Vinyl Soffit Vented - Brushed Finish 32US10VT02

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 75.57 lbs.
Sq. In. Vent Area Per L.F.: 3.8





12" Vinyl Soffit Solid - Brushed Finish 32US12SD02

Length 12' - 0" | 16 Panels/Ctn. - Solid | 192 Sq. Ft./Ctn. | Ctn. Weight: 71.92 lbs.

12" Vinyl Soffit Vented - Brushed Finish 32US12VT02

Length 12' - 0" | 16 Panels/Ctn. | 192 Sq. Ft./Ctn. | Ctn. Weight: 70.66 lbs.
Sq. In. Vent Area Per L.F.: 4.0



12" Vinyl Soffit Center Vented - Brushed Finish 32US12CV02

Length 12' - 0" | 16 Panels/Ctn. | 192 Sq. Ft./Ctn. | Ctn. Weight: 71.50 lbs.
Sq. In. Vent Area Per L.F.: 1.3

Note: All Universal Soffit is Available in **02** White Birch ONLY

Universal Vinyl Soffit

SCI® Siding Vinyl Soffit meets or exceeds all industry standards per ASTM D3679.

Product Test Data

Soffit Thickness.....	.038" ± .001"	Impact Resistance.....	Passes per ASTM D3679
Specific Gravity.....	1.45	Surface Distortion @ 140°F.....	0
Tensile Strength (PSI).....	7,154	Fire Rating	Class A
Tensile Modulus (PSI).....	416,900	Flame Spread Index.....	10
IZOD Impact Strength @ 32°F.....	Passes per ASTM D3679	Smoke Developed.....	.395
Heat Deflection Temp. @ 264 PSI.....	169°F	Fuel Contribution.....	0
Coefficient of Linear Expansion.....	3.30 x 10 ⁻⁵	Average Time Of Burning.....	Self extinguished
Warpage.....	0.00"	Average Extent Of Burning.....	2.379 mm
Heat Shrinkage.....	0.3%	Weathering.....	Passes per ASTM D3679